

DERWENT-ACC-NO: 2004-531392

DERWENT-WEEK: 200451

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: White porous polyester film for surface light
source-reflecting plate

INVENTOR: JU, J S; LEE, G H ; RYU, S H

PATENT-ASSIGNEE: SKC CO LTD[SKCSN]

PRIORITY-DATA: 2002KR-0052877 (September 3, 2002)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE
PAGES MAIN-IPC		
KR 2004021274 A	March 10, 2004	N/A
000 C08L 067/00		

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO
APPL-DATE		
KR2004021274A	N/A	2002KR-0052877
September 3, 2002		

INT-CL (IPC): C08L067/00

ABSTRACTED-PUB-NO: KR2004021274A

BASIC-ABSTRACT:

NOVELTY - A white porous polyester film for a surface light source-reflecting plate and a surface light source reflecting plate containing the polyester film are provided, to improve the reflectivity and the coverage of the film and to reduce the manufacturing cost of a surface light source reflecting plate.

DETAILED DESCRIPTION - The white porous polyester film comprises 100 parts by weight of the resin comprising 80-95 wt% of a polyester resin and 5-20 wt% of a polypropylene resin; 0.2-1.0 parts by weight of a compatibilizer; 1-10 parts by weight of an inorganic fine particle having a diameter of 0.01-1

micrometers;
and 0.01-0.2 parts by weight of a whitening agent. The white porous polyester
film has a reflectivity of an average 90 % or more at a wavelength
range of
400-700 nm, L asterisk of 95.00 or more and b asterisk of -3.00 or
less in
CIELAB system, and a density of 0.8-1.3 g/cm³.

CHOSEN-DRAWING: Dwg.0/0

TITLE-TERMS: WHITE POROUS POLYESTER FILM SURFACE LIGHT SOURCE REFLECT
PLATE

DERWENT-CLASS: A17 A23

CPI-CODES: A05-E01D; A12-L03;

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C2004-195540